



HUZHOU CHIMIQUE IMP. & EXP. CO., LTD.

Add: NO.301, SECTION 1, BUILDING 8, CUIYUAN DISTRICT, WUKANG TOWN, DEQING COUNTY, ZHEJIANG PROVINCE, CHINA

Tel 86 572 8284128 Fax 86 572 8283316

Email: huzhouchimique@gmail.com

TECHNICAL DATA

| | | | | |
|--------------------------------|-------------------------------------------------------------|-------------------|------------|----------------------|
| Product name | Iron oxide yellow 910 | | | |
| Chemical name | Iron hydroxide oxide (α -FeOOH) | | | |
| Delivery form | Powder | | | |
| Color index | Pigment yellow 42 (77492) | | | |
| CAS No./EC No. | 20344-49-4/243-746-4 | | | |
| Specifications | Contents (α -FeOOH) | % | ≥ 86 | ISO1248 |
| | Oil absorption | ml/100g | 25~35 | ISO787-5 |
| | Res. on 325 mesh | % | ≤ 0.3 | ISO787-7 |
| | Water soluble salts | % | ≤ 0.3 | ISO787-3 |
| | Moisture | % | ≤ 1.0 | ISO787-2 |
| | pH value | | 3~7 | ISO787-9 |
| | Ignition loss (1,000°C 1/2h) | % | ≤ 14 | DIN55913 |
| | Bulk density | g/cm ³ | 0.4~0.6 | ISO787-11 |
| | Specific gravity | g/cm ³ | 4.1 | ISO787-10 |
| | Particle size BET | μ m | 0.1x0.6 | Electron Micrographs |
| | Dispersibility (Hegman) | μ m | 20/25/30 | ISO787-20 |
| | Tinting Strength (Compared with Standard) | % | 95~105 | ISO787-24 |
| | Color Difference ΔE (Compared with Standard) | | ≤ 0.8 | ISO787-1 |
| Sales packing | In 25kgs paper bag / 650kg jumbo bag with palletized | | | |
| Transport & Storage | Protect against weathering / Store in a dry place | | | |
| Safety | The product is not classified as dangerous under 67/548/EC. | | | |